

## Description

- Maximum conformity
- Good adhesion to open and closed cell foam surfaces
- High initial tack
- Excellent peel adhesion and strength
- 83# Poly coated Kraft liner

## Physical Properties

<b>Adhesive Thickness</b>		<b>Mils</b>	<b>3.0</b>
<b>Liner Thickness</b>		<b>Mils</b>	<b>6.2</b>
<b>Adhesion: 90°, 2 Mil AL foil, 72 hr RT</b>	<b>ASTM D 3330</b>	<b>Oz/in</b>	<b>--</b>
Stainless Steel			65
Aluminum			46
ABS			34
Polypropylene			35
<b>Static Shear Strength: 1 In<sup>2</sup>, 1,000 g, 72 hr dwell @ 72°F</b>	<b>ASTM D 3654, Modified</b>	<b>Minutes</b>	<b>10,000+</b>
<b>Static Shear Strength: 1 In<sup>2</sup>, 1,000 g, 72 hr dwell @ 158°F</b>	<b>ASTM D 3654, Modified</b>	<b>Minutes</b>	<b>1,126</b>
<b>Service Temperature</b>		<b>°F</b>	<b>-40 to 170</b>
<b>Short Term High Temperature</b>		<b>°F</b>	<b>225</b>
<b>Humidity Resistance: 7 days @ 90°F and 90% RH</b>			<b>No significant reduction in bond strength</b>
<b>Application Temperature</b>		<b>°F</b>	<b>70 to 100</b>

PLEASE NOTE THAT ALL DATA SHEETS ARE SUPPLIED BY LAMATEK, INC. WITH THE UNDERSTANDING THAT THE PURCHASER MUST DETERMINE THE SUITABILITY OF A PARTICULAR PRODUCT FOR ITS INTENDED PURPOSE. UNLESS OTHERWISE STATED, LAMATEK, INC. CANNOT WARRANT PRODUCTS IN THEIR APPLICATION.