

Specifications

- Closed Cell Cork Composition is a highly resilient and compressible material produced from natural cork.
- Applications include shipping pads, gaskets, memo-boards, mats, thermal and acoustic insulation, and vibration insulation.
- Natural color
- Available in tapes or die cut, plain, with Adherence Foam or self-adhesive.

Physical Properties

Physical Property	Test Method	Unit	Value
Density	ASTM F1315	kg/m ³	160 min.
Tensile Strength	ASTM F152, Method B	MPa	0.28 min.
Compressibility @ 100 psi	ASTM F36, Procedure F	%	35-55
Recovery	ASTM F36, Procedure F	%	75 min.
Flexibility (as received)	ASTM F147		F = 8
Boiling Water, 3 Hrs.	ASTM F148, Procedure A		No Disintegration

PLEASE NOTE THAT ALL DATA SHEETS ARE SUPPLIED BY LAMATEK, INC. WITH THE UNDERSTANDING THAT THE PURCHASER MUST DETERMINE THE SUITABILITY OF A PARTICULAR PRODUCT FOR ITS INTENDED PURPOSE. UNLESS OTHERWISE STATED, LAMATEK, INC. CANNOT WARRANT PRODUCTS IN THEIR APPLICATION.