

Specifications

- Commercial blended neoprene
- Matte Finish one side
- ASTM D 2000 1BC 810
- SAE J200 1BC 810
- MIL R 3065 SC 810

Physical Properties

Physical Property	Test Method	Unit	Value
Specific Gravity		g/cc	1.46
Hardness		Shore A	80 +/-5
Color			Black
Tensile Strength	ASTM D 412	psi	1000
Elongation	ASTM D 412	%	100
Compression Set: 22 hrs @ 100°C	ASTM D 395B	%	80 max
Temperature Range		°F	-20 to 170

PLEASE NOTE THAT ALL DATA SHEETS ARE SUPPLIED BY LAMATEK, INC. WITH THE UNDERSTANDING THAT THE PURCHASER MUST DETERMINE THE SUITABILITY OF A PARTICULAR PRODUCT FOR ITS INTENDED PURPOSE. UNLESS OTHERWISE STATED, LAMATEK, INC. CANNOT WARRANT PRODUCTS IN THEIR APPLICATION.