

Specifications

- Low Density, Open Cell Polyurethane Ether Foam
- Charcoal in color
- Supplied Compressed in rolls.

Physical Properties

Physical Property	Test Method	Unit	Value
Density	ASTM D3574	PCF	1.2 +/-10%
Tensile Strength	ASTM D3574	PSI	12.0 min
Elongation	ASTM D3574	%	130 min
Tear Resistance	ASTM D3574	PLI	1.40 min
Compression Force Deflection: 25%	ASTM D3574	PSI	0.30 min
Indentation Force Deflection: 65%	ASTM D3574	LBS/50 SQ. IN	35 min
Retention of Tensile Strength after 22 hours, 140° C, Dry Heat Aging		%	70 min
Retention of Tensile Strength after 5 hours, 120° C, Steam Autoclave		%	70 min

Meets the requirements of RoHS through June 2013 Revision of SVHC

PLEASE NOTE THAT ALL DATA SHEETS ARE SUPPLIED BY LAMATEK, INC. WITH THE UNDERSTANDING THAT THE PURCHASER MUST DETERMINE THE SUITABILITY OF A PARTICULAR PRODUCT FOR ITS INTENDED PURPOSE. UNLESS OTHERWISE STATED, LAMATEK, INC. CANNOT WARRANT PRODUCTS IN THEIR APPLICATION.